





<b>DESCRIPTION</b>			
Total thickness	EN ISO 24346	mm	2.00
Weight	EN ISO 23997	g/sq.m	2985
Width of sheet	EN ISO 24341	cm	200
Length of sheet	EN ISO 24341	lm	20
<b>CLASSIFICATION</b>			
Standard / Product specification	-	-	EN ISO 10581
European classification	EN ISO 10874	[class]	34 - 43
Fire rating	EN 13501-1	[class]	Bfl-s1
Electrical resistance *	EN 1081	Ohm	$10^4 \leq R_t \leq 10^6$
Static electrical propensity	EN 1815	kV	< 2
Slip resistance	DIN 51130	[class]	R9
<b>PERFORMANCE</b>			
Type Binder content	ISO 10581	type	I
Dimensional stability	EN ISO 23999	%	$\leq 0,40$
Residual indentation (norm)	EN ISO 24343-1	Mm	$\leq 0.10$
Residual indentation (average measured value)	-	mm	~ 0,02
Castor chair test (type W)	ISO 4918	-	OK
Thermal conductivity	EN ISO 10456	W/(m.K)	0.25
Colour fastness	EN 20 105 - B02	[degree]	$\geq 6$
Surface treatment	-	-	Evercare™
Chemical products resistance	EN ISO 26987	-	OK
Anti-bacterial activity (E.coli – S. aureus – MRSA) (1)	ISO 22196	-	> 99 % inhibits growth
Antiviral activity (human coronavirus 229E)	ISO 21702	-	99.7% after 2h 99.9% after 5h
<b>ENVIRONMENT / INDOOR AIR QUALITY</b>			
TVOC after 28 days	ISO 16000-6	$\mu\text{g}/\text{m}^3$	< 10
Certification	-	-	Floorscore®
<b>MARQUAGE CE</b>			
	EN 14041	-	 $\leq 10^6 \Omega$   DS
		-	 Bfl-s1