






Grabo Muravyl

Technical parameter	Standard	Unit	Result
DESCRIPTION			
Construction			compact heterogeneous
Total thickness	EN ISO 24346	mm	1.5
Wear layer thickness	EN ISO 24340	mm	0.5
Width of roll	EN ISO 24341	m	2
Length of roll	EN ISO 24341	lm	25
Total weight	EN ISO 23997	kg/m ²	1.4
CLASSIFICATION			
Product specification	EN 649		✓
Residual indentation	EN 433	max. mm	0.1
Dimensional stability	EN ISO 23999	max.%	0.2
Light fastness	EN ISO 105-B02	grade	6
PERFORMANCE			
Abrasion group	MSZ EN 660-1	class	T
Fire resistance	EN 13501-1	class	B-s2,d0
Chemical resistance	EN ISO 26987		✓
Anti-bacterial and fungicid treatment			graboSAN
Enviromental attributes		 	Phthalate-, Solvent- and Heavy metal free product
Seaming method			heat or cold weld